



StoPowerwall Stucco is a controlled blend of Portland cement, fibers and chemical additives. StoPowerwall Stucco, when combined with sand and water at the job site, performs like traditional stucco, with enhanced strength and durability. StoPowerwall Stucco is suitable for use in residential and commercial wall construction over prepared concrete and masonry surfaces or over metal plaster bases.

Technical Data

TEST	TEST METHOD	TEST CRITERIA	TEST RESULTS
Compressive Strength (psi)	ASTM C-109	28 days	> 3,000
Flexural Strength (psi)	ASTM C-293	28 days	> 600
Tensile Strength (psi)	ASTM C-190	28 days	> 200
Shrinkage	ASTM C-157	Air cure 28 days	> 0.09%
Accelerated Weathering	ASTM G-26	2,000 hours	No chalking, cracking, checking, crazing, or erosion
Freeze-Thaw	ICBO AC 11	10 cycles	No cracking, checking, or crazing
Surface Burning	ASTM E-84	Flame spread: < 25 Smoke developed: < 450	Flame spread: < 5 Smoke developed: < 10
Fire Resistance	ASTM E-119	One hour fire resistive rating	Pass, refer to SBCCI PST & ESI Report No. 9838B and ICBO ES Report No. 3899 for listed assemblies
Wind Loads	ASTM E-330	Allowable design pressure	Refer to SBCCI PST & ESI Report No. 9838B for assemblies

Notes: Final strength characteristics are dependent on jobsite variables such as water/cement ratio, mixing, application, drying conditions and moist curing. Refer to the appropriate Sto Product Bulletin for performance data on Sto finishes for use over StoPowerwall Stucco.

Coverage

3/8" (9.5 mm) thick - 60-80 ft² (5.6-7.4 m²) per bag.

1/2" (12.7 mm) thick - 50-68 ft² (4.6-6.3 m²) per bag.

Coverage may vary depending on application technique and surface conditions.

Packaging

80 lb. bag (36 kg).

Shelf Life

12 months, if properly stored and protected from moisture.

Storage

Store off the ground in a dry area. Protect from extreme heat [90°F (32°C)], moisture, direct sunlight and freezing.

Features	Benefits
1 Fiber-reinforced	Resists cracking; high flexural strength
2 Powerwall™ application	Reduces labor costs
3 Concentrate	Economical; easier to transport to job site
4 Thin and lightweight	Reduced structural requirements

103 StoPowerwall™ Stucco

Surface Preparation

Concrete and masonry surfaces: Surfaces must be slightly scarified and free of all bond-inhibiting materials, including dirt, efflorescence, form oil and other foreign matter. Loose or damaged material must be removed and repaired. Dampen surface prior to application of stucco.

Wood or metal frame construction:
Galvanized diamond mesh lath or welded wire

fabric must be securely attached to construction. Refer to StoPowerwall Stucco code report for specific assemblies.

Refer to ASTM C-926 for complete details on preparation and required condition of surfaces to receive Portland cement stuccos and recommended construction practices when installing stuccos.

Mixing

Use approximately 4 gallons (15 L) of clean water and 200 lbs. (90 kg) of washed plaster sand

(ASTM C-897) with each 80 lb. (36 kg) bag of StoPowerwall Stucco. Avoid using excess water.

Application

Surface and ambient temperatures must be above 40°F (4°C) during application and for 24 hours following set of stucco.

Apply with proper spray equipment or a stainless steel trowel, and only to sound and clean, dry, properly prepared, frost-free surfaces. Consult equipment manufacturer for spray/pump application.

Metal Plaster Bases: Must be installed in conformance with ASTM C-1063 or applicable code evaluation report.

Concrete and Masonry: Apply StoPowerwall Stucco with proper spray equipment or a stainless steel trowel in one or two coats to a maximum thickness of 1/2 inch (13 mm).

Metal Plaster Bases: Apply in one or two coats a minimum total thickness of 1/2 inch (13 mm), maximum total thickness of 7/8 inch (22 mm).

Two Coat Applications: Scratch the first coat horizontally and apply the second coat as soon as the first coat is firm enough to receive it.

Alternatively, moist cure the first coat up to 48 hours and dampen the scratched surface with water immediately before applying the second coat.

Level the stucco surface with a darby or stainless steel trowel to achieve a smooth, plumb surface.

Follow practices outlined in ASTM C-296 when installing StoPowerwall Stucco.

Curing/Drying

Moist cure by lightly fogging the installed area for at least 48 hours after the stucco takes initial set (usually within the first 1 to 4 hours after installation). Hot, dry, or windy weather requires more frequent moist curing to avoid rapid dehydration of stucco. Allow final stucco application to completely dry before applying primer or finish.

Clean Up

Clean tools and equipment with water immediately after use. Cured material can only be removed mechanically.

Limitations

- Do not install StoPowerwall Stucco over stucco accessories or joints in construction.
- Do not install at temperatures below 40°F (4°C).
- Not recommended as a finish coating.
- Some cracking and efflorescence are inherent in Portland cement stuccos. These are not product defects.
- For complete information on StoPowerwall Stucco, see Sto Specification S501 and SBCCI PST & ESI Report No. 9838B, or ICBO Evaluation Report No. 3899.

Health And Safety

Health Precautions

Contains Portland cement and crystalline-free silica. Avoid breathing dust. As with any chemical construction product, exercise care when handling.

Safety Precautions

Use adequate ventilation. Use of a NIOSH/MSA approved dust respirator, safety goggles and protective gloves is recommended.

First Aid

SKIN CONTACT: Wash thoroughly with soap and water.
EYE CONTACT: Flush immediately with water for 10-15 minutes and contact a physician.

RESPIRATORY PROBLEMS: Remove affected person to fresh air immediately and contact a physician.

HYGIENE: Wash hands immediately after use. Wash clothing before re-use.

Spills

Collect in an appropriate container. Uncured material may be removed with water.

Disposal

Dispose of in accordance with local, state or federal regulations.

Warning

KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF THE REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. Consult the Material Safety Data Sheet for further health and safety information.

LIMITED WARRANTY

THIS PRODUCT IS SUBJECT TO A WRITTEN LIMITED WARRANTY WHICH CAN BE OBTAINED FREE OF CHARGE FROM: Sto Corp., 3800 Camp Creek Parkway, Building 1400, Suite 120, Atlanta, GA 30331; Tel: 404-346-3666; Fax: 404-346-3119.

Refer to Sto Specifications for more complete information on proper use and handling of these products.

ATTENTION

This product is intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. It should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of this product or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to this product, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESSED OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, www.stocorp.com.

Sto Corp.

3800 Camp Creek Parkway
Building 1400, Suite 120
Atlanta, GA 30331
Tel: 404-346-3666
Toll Free: 1-800-221-2397
Fax: 404-346-3119
www.stocorp.com

S155-103 03/08 VEN 5609

