


# StoSilco® Lit



# 136, 137 & 138

Division 7

136 StoSilco® Lit 1.0  
137 StoSilco® Lit 1.5  
138 StoSilco® Lit R1.5



*StoSilco® Lit is a silicone enhanced textured wall coating designed for use as a finish coat over prepared vertical concrete, masonry or plaster substrates and in StoTherm™ Premier Wall Claddings, including StoTherm Premier NExt™. StoSilco® Lit is a decorative and protective wall coating used for both restoration and new construction. StoSilco® Lit is available in two textures and various aggregate sizes.*

*StoSilco® Lit is enhanced by the addition of Optilink®, a remarkable polymer technology development by Sto that improves the curing and film formation process.*

### Coverage

StoSilco® Lit 1.0: 145-165 ft<sup>2</sup>  
(13.5-15.3 m<sup>2</sup>)  
StoSilco® Lit 1.5: 120-145 ft<sup>2</sup>  
(11.1-13.5 m<sup>2</sup>)  
StoSilco® Lit R 1.5: 135-155 ft<sup>2</sup>  
(12.5-14.4 m<sup>2</sup>)

Coverages may vary depending on application technique and surface conditions.

### Packaging

5 gal. pail (19 L)

### Shelf Life

12 months if properly stored and sealed.

### Storage

Protect from extreme heat [90°F (32°C)], freezing, and direct sunlight.

## Technical Data

TEST	METHOD	CRITERIA	RESULTS
<b>Surface Burning</b>	ASTM E-84	< 25 Flame Spread < 450 Smoke Developed	0 15
<b>Flexibility</b>	ASTM D-522	4" mandrel bend	Pass
<b>Water Vapor Transmission</b> (U. S. perms)	ASTM E-96 Modified	28 days	42
<b>Accelerated Weathering</b>	ASTM G-53	2000 hours	No deleterious effects @ 5000 hrs
<b>Chalk Rating</b>	ASTM D-4214	2000 hours 5000 hours	9 (10 = best on scale 1-10) 8
<b>Yellowness Index</b>	ASTM E-313	5000 hours	.77 (0 = no change; 2 = barely discernable change)
<b>Freeze-thaw Resistance</b>	EIMA 101.01	60 cycles	No deleterious effects @ 90 cycles
<b>Mildew Resistance</b>	ASTM D-3273	No growth @ 28 days	No growth @ 60 days
<b>Salt Spray Resistance</b>	ASTM B-117	300 hours	No deleterious effects @ 700 hrs
<b>Wind Driven Rain</b>	Fed TT-C-555B	24 hour driving rain	No water penetration
<b>Water Resistance</b>	ASTM D-2247	14 days	No deleterious effects @ 42 days
<b>Abrasion Resistance</b>	ASTM D-968	528 qts. sand	No cracking, checking or loss of film integrity @ 1057 qts.
<b>Adhesion (psi)</b>	ASTM D-4541	28 days	> 120 to concrete
<b>VOC (g/L)</b>	Calculated		18 (27*)

\* Less water and exempt solvents

## Features

## Benefits

<b>1 Hydrophobic</b>	Repels water; resists wind driven rain
<b>2 Silicone enhanced</b>	Superior resistance to dirt and airborne pollutants, mildew and algae growth; lowest maintenance
<b>3 Superior vapor permeability</b>	Allows substrate to breathe naturally, resists blisters caused by trapped water vapor
<b>4 Ready-mixed</b>	Ready to use; no additive needed
<b>5 Water-based</b>	Safe, non-toxic; cleans up with water
<b>6 Sto Optilink® advanced polymer technology</b>	Higher resistance to dirt pick-up, mildew, and algae growth; easier to apply and texture
<b>7 Low VOC</b>	Meets South Coast Air Quality Management District Requirements



# 136, 137 & 138 StoSilco® Lit

## Surface Preparation

**Concrete and masonry surfaces:** Surfaces must be free of all bond-inhibiting materials, including dirt, efflorescence, form oil and other foreign matter. Loose or damaged material must be removed by waterblasting, sandblasting or mechanical wire brushing and repaired. Avoid application over irregular surfaces. Resurface, patch or level surfaces to required tolerance and smoothness with appropriate Sto leveling materials. Refer to ASTM D-4258 and ASTM D-4261 for complete details on methods of preparing cementitious substrates for coatings.

**StoTherm™ Exterior Insulation and Finish Systems (EIFS):** Surface must be free of all bond-inhibiting materials.

Sto recommends priming cementitious substrates using the appropriate Sto primer prior to application of finish.

**Gypsum wallboard surfaces:** Wallboard must be taped and fasteners spotted with joint compound. Refer to ASTM C-840 and gypsum wallboard manufacturer's literature. Surface must be free of dust, dirt and other bond-inhibiting materials. Surface must be primed with appropriate Sto Primer.

## Mixing

Mix with a clean, rust-free electric drill and paddle. A small amount of clean water may be

added to aid workability. Limit addition of water to amount needed to achieve the finish texture.

## Application

Apply only to sound and clean, dry, properly prepared, frost-free surfaces.

Apply StoSilco® Lit with a clean stainless steel trowel to a rough thickness slightly more than the largest aggregate size. Use the trowel to scrape the material down to a uniform thickness no greater than the largest aggregate size. Achieve final texture by floating with the appropriate trowel in a figure eight motion; stainless steel trowel for StoSilco® Lit (pebbled texture finishes) and plastic float for StoSilco® Lit R (rilled texture finishes). Once applied, the working time is up to 20 minutes depending upon material, ambient temperatures and surface conditions.

**Spray:** Apply StoSilco® Lit with a hand-held gravity-feed hopper-type sprayer, texture spray pump machine, or other appropriate equipment such as StoSilco® System or Sto's M-8 Spray Pump. Apply an even coat to ensure full coverage of the surface. (Spray application is not recommended for StoSilco® Lit R [rilled texture] finish.)

**IMPORTANT:** ALWAYS check color for proper match. If color does not match, STOP—call your Sto representative. For best results always prime cementitious substrates. Apply coating in a contin-

uous application, always working from a wet edge or architectural break to eliminate cold joints. Minor shade variations may occur from batch to batch (refer to batch no. on pail). Avoid installing separate batches side-by-side and avoid application in direct sunlight. Avoid installing new finish adjacent to weathered or aged finish. Sto Corp. will not be responsible for shade or color variation from batch to batch, variation caused by application or substrate deficiencies, or fading resulting from natural causes such as weather. See Tech Hotline Nos. 0694-C, 0893-EC and 1202-CF for helpful tips on prevention of color problems.

Protect installed product from rain, freezing, and continuous high humidity until completely dry.

### Curing/Drying

StoSilco® Lit Finishes dry within 24 hours under normal conditions [70°F (21°C), 50% RH]. Drying time varies with temperature/humidity and surface conditions.

### Clean Up

Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

## Health And Safety

### Health Precautions

Product is water-based. As with any chemical construction product, exercise care when handling.

### Safety Precautions

Use adequate ventilation. Safety goggles and protective gloves are recommended. Remove contaminated clothing immediately.

### First Aid

**SKIN CONTACT:** Wash thoroughly with soap and water.

**EYE CONTACT:** Flush immediately with water for 10-15 minutes and contact a physician.

**RESPIRATORY PROBLEMS:** Remove affected person to fresh air immediately and contact a physician.

**HYGIENE:** Wash hands immediately after use. Wash clothing before re-use.

### Spills

Collect with suitable absorbent material such as cotton rags.

### Disposal

Dispose of in accordance with local, state or federal regulations.

### Warning

KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. Consult the Material Safety Data Sheet for further health and safety information.

### LIMITED WARRANTY

THIS PRODUCT IS SUBJECT TO A WRITTEN LIMITED WARRANTY WHICH CAN BE OBTAINED FREE OF CHARGE FROM: Sto Corp., 3800 Camp Creek Parkway, Building 1400, Suite 120, Atlanta, GA 30331; Tel: 404-346-3666; Fax: 404-346-3119

### ATTENTION

This product is intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. It should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of this product or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to this product, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, [www.stocorp.com](http://www.stocorp.com).

## Limitations

- Use StoSilco® Lit only when surface and ambient temperatures are above 40°F (4°C) and below 100°F (38°C) during application and drying period.
- For Exterior Insulation and Finish Systems (EIFS), select finish colors with a lightness value of 20 or greater.

- StoSilco® Lit should not be used on weather-exposed horizontal, below grade or water immersed surfaces.
- Sloped surfaces: refer to Sto details.

### Sto Corp.

3800 Camp Creek Parkway  
Building 1400, Suite 120  
Atlanta, GA 30331  
Tel: 404-346-3666  
Toll Free: 1-800-221-2397  
Fax: 404-346-3119  
[www.stocorp.com](http://www.stocorp.com)



100% ACRYLIC  
POLYMERS

S155-136/137/138 02/07 VEN 5609

sto