


## PRODUCT BULLETIN

# Sto Bonding & Pointing Mortar

Product Number: 81711



## PRODUCT DESCRIPTION

Sto Bonding & Pointing Mortar is an integrally colored organic mortar. Use it to install StoCast Brick in Sto proprietary wall systems and over prepared vertical above grade concrete, concrete masonry (CMU), and stucco walls, ceilings, and soffits.

FEATURES	BENEFITS
Organic bonding and pointing mortar	Greatly reduces the risk of efflorescence associated with portland cement-based masonry mortars
Available in nine standard colors	Design flexibility
Easy to install	Does not require highly skilled labor force, cost effective
Made with Acrylic Polymers	Durable, Freeze/Thaw and UV resistant, superior flexural strength; resists cracking

**Coverage (per pail):** 65 - 80 ft<sup>2</sup> (6.3 - 7.4 m<sup>2</sup>)

Coverage may vary depending on substrate, application technique, waste factor, and other variables that may exist.

### Colors:

2057, Anthracite  
 2064, Brown  
 2063, Brown-Grey  
 2061, Graphite  
 2060, Grey  
 2059, Light Grey  
 2062, Sand Yellow  
 2056, White  
 2058, Cement-Grey

Custom colors available.

**Packaging:** 55 lb (25 kg) Pail

**Shelf Life:** 12 months in original, unopened, properly stored container.

**Storage:** Store off the ground in a dry area. Store between 50 and 85°F (10 -29°C). Protect from extreme heat, freezing and direct sunlight.

## SURFACE PREPARATION

Sto Proprietary Wall Systems: StoTherm<sup>®</sup> ci, StoVentec<sup>®</sup>, StoPowerwall<sup>®</sup>, StoQuik<sup>®</sup> Silver, StoPanel<sup>®</sup>, and StoLite<sup>®</sup> systems. Refer to applicable Sto Specification.

Concrete, concrete masonry (CMU), and portland cement stucco: must be constructed in conformance with applicable building code requirements. All surfaces must be structurally sound, clean, dry, and free of frost and surface contamination such as dust, dirt, salts, grease, oils, efflorescence, mold, algae, mildew, and any other contamination that may affect adhesion. Use appropriate repair methods for the substrate to repair pitting, spalls, cracks, peeling, blistering, delamination, weak surface conditions such as laitance, water damage, or other defects that may exist. Skim coat concrete, CMU, and stucco surfaces with Sto BTS Plus up to 1/8 inch (3mm) thick to level/fill the surface or use Sto Leveler and Skim Coat up to ¼ inch (6mm) in one coat or ½ inch (13mm) in two coats. Verify bond to properly prepared surfaces as specified by design professional at 28-day age of the assembly.

## APPLICATION

- Select StoCast Brick from different cartons so brick shades are intermingled as they are installed.
- Plan the layout carefully, taking into account brick pattern, openings such as windows and doors, and alignment of horizontal mortar joints around the building walls.
- Use snips or shears to cut bricks to size as needed
- Curved Surfaces: bricks must be warm to bend them. If necessary, heat bricks and bend to desired curvature. Then install bricks in the mortar. Note: minimum radius for curved surfaces is 4-3/4" (120mm).
- Always construct a mock-up under actual conditions of use to verify proper surface preparation, coverage, and aesthetics, for approval by the appropriate authority.
- Apply only when substrate and ambient temperatures are between 50 to 100°F (5-38°C) over prepared surfaces. Do not apply over damp surfaces or during rain, hail, or snow events, or if rain, hail, or snow is imminent.
- During hot weather keep material in a cool location just prior to use and work in shade. Spread mortar in smaller areas, install StoCast Brick units immediately, and tool mortar before it "skins." If mortar "skins" cracks, or "cakes," remove it and apply fresh material.

## PRODUCT BULLETIN

---

# Sto Bonding & Pointing Mortar

Product Number: 81711

### APPLICATION (CONTINUED)

1. Establish layout lines for the pattern in use (e.g., running bond, stacked bond) and mark them on the walls.
2. Place StoCast Brick units from top to bottom in accordance with the planned layout and work from one end to the other, downward in sequential rows.
3. Apply Sto Bonding & Pointing Mortar vertically with a ¼ x ¼ x ¼ inch (6x6x6mm) square notched trowel. Apply in a small area and immediately install StoCast Brick before a “skin” forms on the mortar.
4. Slide and slightly twist the units into the freshly applied mortar while applying pressure to fully bed the units in the mortar and to ensure no gaps or cavities exist in the mortar. Align units visually while progressing down the wall.
5. As soon as the units are held in place with mortar, work the joint areas with a small paint brush or specialized pointing tool before the material “skins” to compact and smooth the mortar, and to create a joint profile that covers the edges of the units.
6. Remove excess mortar from the face of the units with a damp sponge while the mortar is still wet.
7. After mortar is dry, use a suitable hand brush to clean the surface of the units if needed. Carefully use a utility knife to remove any dry mortar remnants on the surface.
8. After mortar is completely dry, touch-up mortar joints if needed to seal edges or to sharpen aesthetics.
9. If thicker joints are desired, wait 7 days, then point mortar joints with additional mortar, and tool to compact the mortar to a concave profile. Clean the surface as described previously.

Refer to *StoCast Brick Application Guide* for more information.

### Clean Up

Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

### Drying

Sto Bonding & Pointing Mortar dries within 24 hours under normal conditions [70°F(21°C), 50% RH]. Drying time varies depending on temperature/humidity and surface conditions. Hot, dry conditions accelerate drying. Cool damp conditions delay drying and may require extended periods of protection from rain and freezing. Protect from rain, freezing and continuous high humidity until completely dry.

### LIMITATIONS

- Minimum radius: 4-3/4 inches (120 mm)
- Use only when surface and ambient temperatures are between 50 to 100°F (5-38°C) during application and drying period.
- Do not use on horizontal or below grade surfaces, projecting ledges, sills, or sloped surfaces, or where immersion in water may occur
- Do not use on roof or roof-like surfaces
- Select colors with Light Reflectance Value (LRV) greater than or equal to 20 when used over StoTherm ci or StoTherm ci XPS Systems (does not apply to StoTherm ci Mineral)

### LIMITED WARRANTY

This product is subject to a written limited warranty which can be obtained free of charge from Sto Corp.

### HEALTH & SAFETY

**Health Precautions:** Product is water-based. As with any chemical construction product, exercise care when handling.

**WARNING:** Causes eye and skin irritation.

**Precautionary Statement:** Wash hands thoroughly after handling.

Wear protective gloves/protective clothing/eye protection/face protection.

**FIRST AID MEASURES:** Eye Contact: Immediately flush eyes with plenty of water for at least 15 to 20 minutes. Ensure adequate flushing of the eyes by separating the eyelids with fingers. Get immediate medical attention.

**Skin Contact:** Immediately wash skin with plenty of soap and water for 15 to 20 minutes, while removing contaminated clothing and shoes. Get medical attention if irritation develops or persists.

**Inhalation:** If inhaled, remove to fresh air. If not breathing, give artificial respiration or give oxygen by trained personnel. Seek immediate medical attention.

**Ingestion:** If swallowed, do NOT induce vomiting. Call a physician or poison control center immediately. Never give anything by mouth to an unconscious person. Store locked up.

**Spills:** Collect with suitable absorbent material such as cotton rags.

**Disposal:** Dispose of in accordance with local, state or federal regulations.

**Warning:** KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF THE REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. Consult the Safety Data Sheet (SDS) on [www.stocorp.com](http://www.stocorp.com) for further health and safety information.

## PRODUCT BULLETIN

# Sto Bonding & Pointing Mortar

Product Number: 81711

### TECHNICAL DATA

REPORT (includes Sto Bonding & Pointing Mortar and StoCast Brick)	TEST METHOD	TEST CRITERIA	TEST RESULT*
Adhesion to Sto base coats	ASTM D1623	> 103 kPa (15 psi)	Pass
Water Vapor Permeance of Lamina	ASTM E96 Method A	Measure	69.18 ng/(Pa•s•m <sup>2</sup> ) (1.21 US Perms)
UV Resistance	ASTM G155	No deleterious effects	Pass
Surface Burning	ASTM E84	Flame Spread: ≤ 25 Smoke Developed: ≤ 450	Flame Spread: 0 Smoke Developed: 20
Radiant Heat Ignition <sup>1</sup>	NFPA 268	No ignition during the 20-minute test period	No ignition
Multistory Flame Spread <sup>1</sup>	NFPA 285	Complies with NFPA 285 Acceptance Criteria	Pass (qualifies for use on noncombustible construction)
Fire Resistance <sup>1</sup>	ASTM E119	Achieves hourly rating	Achieves 1 and 2-hour ratings as a component of StoTherm ci
Building Code Compliance <sup>1</sup>	Class A Building Material: qualifies for use as an interior finish		
	Meets requirements for use on noncombustible construction as a finish component <sup>2</sup> of: <ul style="list-style-type: none"> <li>• StoTherm® ci, StoVentec®, StoPowerwall®, StoQuik® Silver, StoPanel®, and StoLite®</li> <li>• StoVentec® Render Ventilated Rainscreen. Refer to Intertek Design Listing Sto/CWP 30-01</li> <li>• Code compliant concrete, concrete masonry, and portland cement stucco wall assemblies</li> </ul>		
<p>* Results are based on lab testing under controlled conditions. Results can vary between labs or from field tests.</p> <p>1. Results achieved as part of a full wall assembly. Refer to applicable Sto specification for details.</p> <p>2. Complies as finish component based on rational analysis of fire test data.</p>			

### Sto Corp.

3800 Camp Creek Parkway  
 Building 1400, Suite 120  
 Atlanta, GA 30331  
 Tel: 404-346-3666  
 Toll Free: 1-800-221-2397  
 Fax: 404 346-3119  
[www.stocorp.com](http://www.stocorp.com)

Revision Number: 1.4  
 Date: November, 2022

#### ATTENTION

This product is intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. It should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of this product or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to this product, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESSED OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, [www.stocorp.com](http://www.stocorp.com)